

Cooling









Tolerance

-

Coating

BetaUni Iron

Strategy

UNI

Application



Features


HA




Basic



■ For universal chamfering of work pieces



Roughing



Finishing



	D1  mm ø	L1  mm	D2  mm ø	z  #
BCU1-M09-0103				
3	3.0	50.0	3.0	3
4	4.0	50.0	4.0	4
6	6.0	50.0	6.0	4
8	8.0	58.0	8.0	4
10	10.0	66.0	10.0	4
12	12.0	73.0	12.0	4



Download Catalog
Pages (PDF)

 Download Catalog Pages (PDF)			Dimension		Ø3	Ø4	Ø6	Ø8	Ø10	Ø12				
			Infeed in mm	ae=0.1xD ap=L2 max	ae=0.1xD ap=L2 max	ae=0.1xD ap=L2 max	ae=0.1xD ap=L2 max	ae=0.1xD ap=L2 max	ae=0.1xD ap=L2 max					
			Application											
			Material	Strength (N/mm²)	Feed (mm/Z)	fz	fz	fz	fz	fz	fz			
P			Vc (m/min)											
1.1-1.3	Steel, unalloyed	<850	110	0.018	0.024	0.035	0.045	0.055	0.065					
2.1-2.2	Steel, low-alloyed	<950	100	0.015	0.02	0.03	0.04	0.05	0.06					
3.1-3.2	Steel, high-alloyed	<1100	70	0.012	0.016	0.025	0.035	0.045	0.055					
K			Vc (m/min)											
1.1-1.2	Grey cast iron	<1000	95	0.015	0.02	0.03	0.04	0.05	0.06					
M			Vc (m/min)											
1.1	Inox, ferritic/martensitic	<850	75	0.011	0.015	0.023	0.032	0.042	0.05					
2.1	Inox, austenitic	<650	55	0.01	0.014	0.021	0.03	0.04	0.048					
N			Vc (m/min)											
1.1-2.3	Alu, alloyed, casted	<600	280	0.025	0.03	0.04	0.05	0.06	0.07					
3.1-3.3	Cooper, alloyed	<600	150	0.015	0.02	0.03	0.04	0.05	0.06					
T			Vc (m/min)											
2.1-2.2	Titanium, pure, alloyed	<1000	40	0.01	0.014	0.021	0.03	0.04	0.048					
S			Vc (m/min)											
1.1-1.3	Super alloys	<1450	30	0.008	0.012	0.018	0.026	0.035	0.042					
NOTE The values marked in turquoise are side applications!														